

## **Product Data Sheets**

## DOL 1000 GLOSS CLEAR OVERLAMINATE 2 MIL CAST

## **GENERAL DESCRIPTION:**

SMF DOL 1000 Gloss Clear Cast Overlaminates are a premium quality high gloss vinyl film designed as a protecting overlaminate film for screen printed and digital printed decals.

PRODUCT DATA	VALUE		TEST METHOD
Outdoor Durability	Five (5) years <sup>1</sup> (vertical exposure unprinted film)		
Thickness -mil (micron)	Film: 2.1 (54	3-30) +/- 0.1 (3) 4) +/- 10% Bleached Kraft PE coated Print	ISO 4591:1992 ISO 4591:1992 red Grey
<b>Application Surface</b>	Flat, simple curves, irregular with rivets		KPMF ST 22
Service Temp. Range	-40°F to 221°F (-40°C to 105°C)		
Min. Application Temp. <sup>2</sup> 45°F (7°C)		dry surface	
Shelf Life	Two (2) years stored at 73°F (23°C) and 50%+/- 5% R.H.		
Dimensional Stability (%)	-0.016 in. (0.4 mm) On Al panel at 158°F (70°C) for 48 hr.		FTM14/Aluminium
Flammability	Self-extinguishing		
Adhesion Value <sup>3</sup>	24 hrs.  Stainless Steel 74 oz/in (810 N/m)  Aluminium 88 oz/in (970 N/m)  Glass 74 oz/in (810 N/m)  Acrylic Sheet 74 oz/in (810 N/m)  ABS Sheet 63 oz/in (690 N/m)		Untreated
Chemical Resistance	Chemical Anti-freeze (24 hrs.) Detergent (8 hrs.) No SAE 20 Motor Oil (24 hrs.) Gasoline (1 hr.) 10% HCL (10 min.) 10% NH <sub>4</sub> OH (10 min.) Sea Water	Effect No Effect	At 73°F (23°C)  1 year Mid Tide (BS 5609:1986)

<sup>1.</sup> May be reduced by extreme climate exposure. Metallics six (6) years; Colours eight (8) years. 2. Surface/Ambient Air. 3. 180° peel at 23°C