

K71100 Series Crystal Cast Vinyl

These premium quality cast vinyl films are intended for use in all exterior marking and signage applications.

The films have the ultimate properties for outdoor durability and are suitable for graphics on original equipment identification, building signage and vehicle graphics. They are also widely used for train liveries, boats and as overlaminating films to produce a sparkle effect.

The materials are conformable, being able to be used on smooth and gently contoured surfaces, and are available in a variety of colours.

The films are available as: -

K71112 Silk Crystal (50µ)	K71115 White (57µ)	K71155 Pink (57µ)	K71175 Green (57µ)
K71113 Sparkle Crystal (57µ)	K71135 Lemon Yellow (57µ)	K71165 Blue (57µ)	K71185 Bronze (57µ)

CHARACTERISTIC	TEST METHOD	TYPICAL VALUE
Film Thickness	ISO 4591:1992	0.053mm / 0.057mm (see above)
Adhesive Thickness	ISO 4591:1992	0.025mm
Adhesive Type		Clear Permanent Cross-Linking Acrylic
Release Liner		150gsm PE Coated Printed Grey
Storage		Two years, out of direct sunlight at 23°C and 50% humidity
Tensile	ISO 527:1996	>12.0 N/mm ²
Elongation	ISO 527:1996	>50%
Adhesion 20 Mins/90°	FINAT FTM2/Stainless Steel	250 N/Metre
Adhesion 20 Mins/180°	FINAT FTM1/Stainless Steel	300 N/Metre
Adhesion 24 Hrs/180°	FINAT FTM1/Stainless Steel	500 N/Metre
Static Shear (25 x 25mm)	FINAT FTM8/Stainless Steel	>16 hours
Dimensional Stability (150 x 150mm/48 hours/70°C)	FTM14/Aluminium	<0.4mm
Gloss 60°	ASTM 523-89	<20%
Flammability		Self Extinguishing
Artificial Weathering	Atlas Xenon arc	>2000 hours
Weathering	Vertical Exposure/Mid Europe	10-12 Years
Rivet Testing		Not applicable
Application Temperature	KPMF ST 22	+8°C to 25°C
Service Temperature	Clean, dry surface	-40°C to + 105°C
Adhesion Properties to Various Substrates for 24 hours at 23°C/180° Peel		
Glass		500 N/Metre
Acrylic Sheet		500 N/Metre
ABS Sheet		400 N/Metre
Resistance to various liquids after application and conditioned for 24 hours at 23°C. Results examined 1 hour after test.		
Humidity	24 hours at 38°C and 100%	No Effect
Water (Distilled)	24 hours at 32°C	No Effect
Sea Water	1 year Mid Tide (BS 5609:1986)	No Effect
Reference Fuel	1 hour at 23°C	Very Slight Film Softening
Diesel Fuel	1 hour at 23°C	No Effect
SAE Motor Oil	24 hours at 23°C	No Effect
Antifreeze/Water (1:1)	24 hours at 23°C	No Effect
Detergent Solution	8 hours at 65°C	No Effect
Hydraulic Oil	24 hours at 23°C	No Effect
Battery Acid	24 hours at 23°C	No Effect
Although we have good control of the colour production at KPMF, it is advisable to avoid using different batches of material for the same end application		

KPMF films should not be applied to unsound surfaces or to surfaces which may subsequently crack, peel, outgas or are of low surface energy. It is recommended that any application surface should have an energy level in excess of 40 dyne/cm. (Polyolefins should be in excess of 45 dyne/cm). The above data shows typical properties and should not be taken as a guarantee for performance. Purchasers should determine the suitability of each product prior to its intended use. Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids etc. may eventually cause deterioration. Durability is based on middle European exposure conditions. Actual performance will depend on substrate preparation, exposure conditions and application of marking.

IMPORTANT

Kay Premium Marking Films are produced under stringent manufacturing conditions. The information and typical values shown are based upon research believed to be reliable and are provided without guarantee and do not constitute a warranty. The values are not for use in specifications. Ink and paint systems can affect the performance of film and also the adhesive properties, as can application techniques. Users are advised to ensure that performance and reliability are not compromised by determining the suitability of each product prior to its intended use.

WARRANTY

Kay Premium Marking Films are produced under careful quality control and are warranted to be fit for the purpose and free from defect in material and workmanship. Any material shown to be defective to our satisfaction at the point of sale shall be replaced free of charge. Kay Premium Marking Films Limited liability to the purchaser shall in no circumstances exceed the cost of the amount of the defective material supplied.